

PRODUCTION OF LOW POLYMERIC ALPHA-OLEFIN

Patent number: JP10045634
Publication date: 1998-02-17
Inventor: ARAKI YOSHITAKE; NAKAMURA HIROFUMI; NANBA YOSHIAKI; OKANO TAKESHI
Applicant: MITSUBISHI CHEM CORP
Classification:
- international: C07C11/00; B01J31/12; C07C2/26; C07C11/107; C10G50/00
- european:
Application number: JP19960208537 19960807
Priority number(s):

Abstract of JP10045634

PROBLEM TO BE SOLVED: To enable to continuously obtain the subject compound in high yield and selectivity without generating a polymer as a by-product by feeding each component of a chromium-based compound catalyst in a specific rate to a reaction zone at the beginning of a reaction to initiate the reaction of an α -olefin.

SOLUTION: In continuously reacting (B) α -olefin to polymerize into a low polymer using (A) a chromium-based catalyst consisting of a chromium compound (A1), a nitrogen-containing compound (A2) which is an amine, an amide or an imide and an alkylaluminum compound (A3), each component of the component A and the component B are fed to a reaction zone so that each of molar ratios A2/A1 and A3/A1 is made higher than the molar ratio in a stationary state to initiate the low polymerization reaction of the component B. It is preferable to feed each component of the component A and the component B to the reaction zone while keeping A1 and A3 apart not to come into contact with each other, thus, the objective compound can be obtained in high purity.

Data supplied from the esp@cenet database - Patent Abstracts of Japan